

Technical Data Sheet

# Polyflam RIPP 490

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics

**Product Description**

Flame-retardant PP-Copolymer; halogen free

**General**

Features	• Copolymer	• Flame Retardant	• Halogen Free
UL File Number	• E86615		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PP FR(51)		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.04 g/cm <sup>3</sup>	1.04 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°c/2.16 Kg)	9.0 cm <sup>3</sup> /10min	9.0 cm <sup>3</sup> /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	276000 psi	1900 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	3190 psi	22.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	3.0 %	3.0 %	ISO 527-2/1A/50

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°f (-30°c)	1.4 ft·lb/in <sup>2</sup>	3.0 kJ/m <sup>2</sup>	
73°f (23°c)	1.4 ft·lb/in <sup>2</sup>	3.0 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°f (-30°c)	5.2 ft·lb/in <sup>2</sup>	11 kJ/m <sup>2</sup>	
73°f (23°c)	18 ft·lb/in <sup>2</sup>	37 kJ/m <sup>2</sup>	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	226 °F	108 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	136 °F	58.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	162 °F	72.0 °C	ISO 306/B50
--	302 °F	150 °C	ISO 306/A50
Ball Pressure Test (257°f (125°c))	Pass	Pass	IEC 60695-10-2
RTI Elec			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	
RTI Imp			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	
RTI Str			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	

Technical Data Sheet

# Polyflam RIPP 490

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	600 V	600 V	IEC 60112
High Amp Arc Ignition (HAI)			UL 746A
0.06 In (1.5 Mm)	PLC 0	PLC 0	
0.12 In (3.0 Mm)	PLC 0	PLC 0	
Hot-wire Ignition (HWI)			UL 746A
0.06 In (1.5 Mm)	PLC 3	PLC 3	
0.12 In (3.0 Mm)	PLC 0	PLC 0	
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	FMVSS 302
0.0787 In (2.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	ISO 3795
Flame Rating			UL 94 IEC 60695-11-10, -20
0.06 In (1.5 Mm)	V-0	V-0	
0.12 In (3.0 Mm)	V-0	V-0	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1760 °F	960 °C	
0.12 In (3.0 Mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1340 °F	725 °C	
0.12 In (3.0 Mm)	1340 °F	725 °C	
Oxygen Index	36 %	36 %	ISO 4589-2

Technical Data Sheet

# Polyflam RIPP 490

Polypropylene Copolymer  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	158 to 176 °F	70 to 80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	356 °F	180 °C
Middle Temperature	392 °F	200 °C
Front Temperature	410 °F	210 °C
Nozzle Temperature	428 °F	220 °C
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	104 to 176 °F	40 to 80 °C
Injection Pressure	11600 to 17400 psi	80.0 to 120 MPa
Injection Rate	Slow-Moderate	Slow-Moderate
Holding Pressure	725 to 1450 psi	5.00 to 10.0 MPa
Cushion	< 0.197 in	< 5.00 mm
Screw Speed	< 709 in/min	< 18 m/min

**Notes**

These are typical property values not to be construed as specification limits.