

Technical Data Sheet

POLYFORT® PPC MGB6 RD H1

Polypropylene Copolymer
Engineering Plastics

Product Description

Hybrid filled low density PP-Copolymer with excellent scratch resistance, low emission and UV-stability especially for automotive interior parts

General

Filler / Reinforcement	• Glass Bubble	• Mineral
Features	• Good Scratch Resistance	• Low Density
	• Heat Stabilized	• Low Emissions
Processing Method	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	0.900 g/cm ³	0.900 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	10 cm ³ /10min	10 cm ³ /10min	ISO 1133
Molding Shrinkage	0.90 to 1.3 %	0.90 to 1.3 %	ISO 294-4

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	247000 psi	1700 MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	3340 psi	23.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	4.0 %	4.0 %	ISO 527-2/1A/50

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	1.4 ft·lb/in ²	3.0 kJ/m ²	
73°F (23°C)	3.3 ft·lb/in ²	7.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	12 ft·lb/in ²	25 kJ/m ²	
73°F (23°C)	43 ft·lb/in ²	90 kJ/m ²	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	185 °F	85.0 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	131 °F	55.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	277 °F	136 °C	ISO 306/A50
--	140 °F	60.0 °C	ISO 306/B50


Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	2.8 in/min	70 mm/min	ISO 3795
0.0787 in (2.00 mm)	2.8 in/min	70 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	

Technical Data Sheet

POLYFORT[®] PPC MGB6 RD H1

Polypropylene Copolymer
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	446 to 518 °F	230 to 270 °C
Mold Temperature	104 to 158 °F	40 to 70 °C

Injection Notes

Drying normally not necessary.

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.