

Technical Data Sheet

# POLYFORT<sup>®</sup> PPC MT30 HI SF FC

Polypropylene Copolymer  
Engineering Plastics

**Product Description**

30% talc filled high impact PP-Copolymer

**General**

- |                        |                              |
|------------------------|------------------------------|
| Filler / Reinforcement | • Talc, 30% Filler by Weight |
| Processing Method      | • Injection Molding          |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density	1.17 g/cm <sup>3</sup>	1.17 g/cm <sup>3</sup>	ISO 1183/A
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	10 g/10 min	10 g/10 min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Stress (Break)	3630 psi	25.0 MPa	ISO 527
Flexural Modulus	435000 psi	3000 MPa	ISO 178

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Charpy Notched Impact Strength (73°F (23°C))	6.7 ft·lb/in <sup>2</sup>	14 kJ/m <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength 73°F (23°C)	No Break	No Break	ISO 179/1eU

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Heat Deflection Temperature 66 psi (0.45 MPa), Unannealed	257 °F	125 °C	ISO 75-2/Bf
Vicat Softening Temperature	302 °F	150 °C	ISO 306/A50

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
--------------	-------------------------	--------------------	-------------

Burning Rate			
0.0787 in (2.00 mm)	3.1 in/min	80 mm/min	ISO 3795
0.0787 in (2.00 mm)	3.1 in/min	80 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	

Technical Data Sheet

# POLYFORT<sup>®</sup> PPC MT30 HI SF FC

Polypropylene Copolymer  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	446 to 518 °F	230 to 270 °C
Mold Temperature	104 to 158 °F	40 to 70 °C

### Injection Notes

Drying normally not necessary.

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

### Notes

These are typical property values not to be construed as specification limits.