

Technical Data Sheet

Polyflam RIPP 374 ND CS1 5V BLK7103

Polypropylene Copolymer

Product Description

20% talc filled flame-retardant PP-Copolymer; without PBDE UL94 5VA rated

Processing Method	Injection Molding
Attribute	Copper Contact Stabilized
Additive	Flame Retardant
Filler/Reinforcement	Talc, 20%
Resin ID	PP TD20 FR(17)

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Volume Flow Rate, (230 °C/2.16 kg)	5.0	cm ³ /10 min	ISO 1133
Density, (Method A)	1.39	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (Type 1A, 50 mm/min)	20.0	MPa	ISO 527-2
Nominal Tensile Strain at Break, (50 mm/min, Type 1A)	15	%	ISO 527-2
Flexural Modulus, (2.0 mm/min)	2500	MPa	ISO 178
Tensile Strain at Yield, (Type 1A, 50 mm/min)	2.0	%	ISO 527-2
Tensile Stress at Break, (Type 1A, 50 mm/min)	9.00	MPa	ISO 527-2
Tensile Modulus, (1 mm/min, Type 1A)	2400	MPa	ISO 527-1
Flexural Stress			
(2.0 mm/min, 3.5%)	29.0	MPa	ISO 178
(2.0 mm/min, 3.0%)	30.0	MPa	ISO 178
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	10	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise, Notch A)	2.0	kJ/m ²	ISO 179
Charpy Impact Strength - Unnotched			
(23 °C, Type 1, Edgewise)	35	kJ/m ²	ISO 179
(-30 °C, Type 1, Edgewise)	13	kJ/m ²	ISO 179
Hardness			
Ball Pressure Test, (100 °C)	Pass		IEC 60695-10-2
Thermal			
Vicat Softening Temperature			
(B (50N), 50 °C/h)	59.0	°C	ISO 306
(A (10N), 50 °C/h)	137	°C	ISO 306

Deflection Temperature Under Load Unannealed (0.45 MPa), (Flatwise)	83.0 °C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa), (Flatwise)	53.0 °C	ISO 75-2/A
RTI Elec		
(1.5 mm)	65.0 °C	UL 746B
(3.0 mm)	65.0 °C	UL 746B
(0.75 mm)	65.0 °C	UL 746B
(2.0 mm)	65.0 °C	UL 746B
RTI Imp		
(1.5 mm)	65.0 °C	UL 746B
(3.0 mm)	65.0 °C	UL 746B
(0.75 mm)	65.0 °C	UL 746B
(2.0 mm)	65.0 °C	UL 746B
RTI Str		
(1.5 mm)	65.0 °C	UL 746B
(3.0 mm)	65.0 °C	UL 746B
(0.75 mm)	65.0 °C	UL 746B
(2.0 mm)	65.0 °C	UL 746B
Electrical		
Volume Resistivity	>1.0E+13 ohm*m	IEC 62631-3-1
Comparative Tracking Index (CTI)	600 V	IEC 60112
High Amp Arc Ignition		UL 746A
Surface Resistivity	>1.0E+15 ohm	IEC 60093
Flammable		
Hot-wire Ignition (HWI)		UL 746A
Burning Rate		
(2.00 mm, Self-Extinguishing)	0.0 mm/min	FMVSS 302
(2.00 mm, Self-Extinguishing)	0.0 mm/min	ISO 3795
Glow Wire Flammability Index		
(0.75 mm)	960 °C	IEC 60695-2-12
(1.5 mm)	960 °C	IEC 60695-2-12
(3.0 mm)	960 °C	IEC 60695-2-12
Glow Wire Ignition Temperature		
(0.75 mm)	850 °C	IEC 60695-2-13
(1.5 mm)	800 °C	IEC 60695-2-13
(3.0 mm)	800 °C	IEC 60695-2-13
UL Information		
Flame Rating		
(1.5 mm)	V-0	UL 94
(3.0 mm)	V-0	UL 94
(3.0 mm)	5VA	UL 94
(0.75 mm)	V-0	UL 94
(2.0 mm)	5VA	UL 94
Flammability Classification		
(0.75 mm)	V-0	IEC 60695-11-10, -20
(1.5 mm)	V-0	IEC 60695-11-10, -20
(2.0 mm)	5VA	IEC 60695-11-10, -20
(3.0 mm)	V-0	IEC 60695-11-10, -20
(3.0 mm)	5VA	IEC 60695-11-10, -

UL File Number

E86615

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	70 to 80	°C
Nozzle Temperature	220	°C
Screw Speed	<300	mm/sec
Processing (Melt) Temp	180 to 210	°C
Front Temperature	210	°C
Holding Pressure	40.0 to 90.0	MPa
Middle Temperature	200	°C
Rear Temperature	180	°C
Injection Rate	Slow- Moderate	
Back Pressure	5.00 to 10.0	MPa
Mold Temperature	40 to 80	°C
Injection Pressure	80.0 to 120	MPa
Cushion	<5.00	mm