



Technical Data Sheet

# SCHULAREC PP 70/01

Polypropylene Copolymer



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	446 to 518 °F	230 to 270 °C
Mold Temperature	104 to 158 °F	40 to 70 °C

**Injection Notes**

\*Drying normally not necessary.

**Notes**

These are typical property values not to be construed as specification limits.