

Technical Data Sheet

Accutech HP0334M30CL

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General	
Filler / Reinforcement	• Mica, 30% Filler by Weight
Features	• Chemically Coupled
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.12	1.12 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	4.0 g/10 min	4.0 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	508000 psi	3500 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	5080 psi	35.0 MPa	
Break	3920 psi	27.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	10 %	10 %	
Flexural Modulus	508000 psi	3500 MPa	ASTM D790
Flexural Strength	6960 psi	48.0 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.82 ft·lb/in	44 J/m	ASTM D256

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	62	62	ASTM D785

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	252 °F	122 °C	
264 Psi (1.8 Mpa), Unannealed	165 °F	74.0 °C	

Additional Information
Ash Content, ASTM D2584: 30%

Notes

These are typical property values not to be construed as specification limits.