

Technical Data Sheet

Accutech HP0334T10L1

Polypropylene Homopolymer

LyondellBasell Industries

Engineering Plastics

General			
Filler / Reinforcement	• Talc, 10% Filler by Weight		
Forms	• Pellets		
Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.969	0.967 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	203000 psi	1400 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	5370 psi	37.0 MPa	
Break	3480 psi	24.0 MPa	
Tensile Elongation			ASTM D638
Yield	7.0 %	7.0 %	
Break	20 %	20 %	
Flexural Modulus	305000 psi	2100 MPa	ASTM D790
Flexural Strength	6820 psi	47.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.75 ft·lb/in	40 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	96	96	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	234 °F	112 °C	
264 Psi (1.8 Mpa), Unannealed	145 °F	63.0 °C	

Additional Information			
Ash Content, ASTM D2584:	10%		

Notes

These are typical property values not to be construed as specification limits.