

Technical Data Sheet

# Accutech HP0334T40L1

Polypropylene Homopolymer  
 LyondellBasell Industries  
 Engineering Plastics

**General**

- |                        |                              |
|------------------------|------------------------------|
| Filler / Reinforcement | • Talc, 40% Filler by Weight |
| Forms                  | • Pellets                    |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.23	1.23 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	406000 psi	2800 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	4930 psi	34.0 MPa	
Break	4640 psi	32.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	10 %	10 %	
Flexural Modulus	624000 psi	4300 MPa	ASTM D790
Flexural Strength	6820 psi	47.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.56 ft·lb/in	30 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	75	75	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	270 °F	132 °C	
264 Psi (1.8 Mpa), Unannealed	180 °F	82.0 °C	

**Additional Information**

Ash Content, ASTM D2584: 40%

**Notes**

These are typical property values not to be construed as specification limits.