

Technical Data Sheet

Accutech HP0336G20CL

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General

- Filler / Reinforcement
 - Glass Fiber, 20% Filler by Weight
- Forms
 - Pellets

Physical

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.03	1.03 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	7.0 g/10 min	7.0 g/10 min	ASTM D1238

Mechanical

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	435000 psi	3000 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	7830 psi	54.0 MPa	
Break	7830 psi	54.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	5.0 %	5.0 %	
Flexural Modulus	580000 psi	4000 MPa	ASTM D790
Flexural Strength	11200 psi	77.0 MPa	ASTM D790

Impact

	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.79 ft·lb/in	42 J/m	ASTM D256

Hardness

	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	103	103	ASTM D785

Thermal

	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	311 °F	155 °C	
264 Psi (1.8 Mpa), Unannealed	266 °F	130 °C	

Additional Information

Ash Content, ASTM D2584: 20%

Notes

These are typical property values not to be construed as specification limits.