

Technical Data Sheet

# Accutech HP0336T40L1

Polypropylene Homopolymer  
 LyondellBasell Industries  
 Engineering Plastics

**General**

- |                        |                              |
|------------------------|------------------------------|
| Filler / Reinforcement | • Talc, 40% Filler by Weight |
| Forms                  | • Pellets                    |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.22	1.22 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	12 g/10 min	12 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	319000 psi	2200 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	4790 psi	33.0 MPa	
Break	4350 psi	30.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	8.0 %	8.0 %	
Flexural Modulus	580000 psi	4000 MPa	ASTM D790
Flexural Strength	7110 psi	49.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.56 ft·lb/in	30 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	80	80	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	275 °F	135 °C	
264 Psi (1.8 Mpa), Unannealed	180 °F	82.0 °C	

**Additional Information**

Ash Content, ASTM D2584: 40%

**Notes**

These are typical property values not to be construed as specification limits.