

Technical Data Sheet

# Accutech HP0339G20M10CL

Polypropylene Homopolymer  
 LyondellBasell Industries  
 Engineering Plastics

General	
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight • Mineral, 10% Filler by Weight
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.11	1.11 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°c/2.16 Kg)	9.0 g/10 min	9.0 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	522000 psi	3600 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	7690 psi	53.0 MPa	
Break	7690 psi	53.0 MPa	
Tensile Elongation			ASTM D638
Yield	4.0 %	4.0 %	
Break	6.0 %	6.0 %	
Flexural Modulus	653000 psi	4500 MPa	ASTM D790
Flexural Strength	11700 psi	81.0 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.94 ft·lb/in	50 J/m	ASTM D256
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	92	92	ASTM D785
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	309 °F	154 °C	
264 Psi (1.8 Mpa), Unannealed	271 °F	133 °C	

Additional Information	
Ash Content, ASTM D2584:	30%

**Notes**

These are typical property values not to be construed as specification limits.