

Technical Data Sheet

Accutech HP0339W30L

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General

Filler / Reinforcement	• Wollastonite (CaSiO ₃), 30% Filler by Weight
Forms	• Pellets

Physical

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	21 g/10 min	21 g/10 min	ASTM D1238

Mechanical

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	435000 psi	3000 MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	4500 psi	31.0 MPa	
Break	4060 psi	28.0 MPa	
Tensile Elongation			ASTM D638
Yield	5.0 %	5.0 %	
Break	12 %	12 %	
Flexural Modulus	479000 psi	3300 MPa	ASTM D790
Flexural Strength	6090 psi	42.0 MPa	ASTM D790

Impact

	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact	0.56 ft·lb/in	30 J/m	ASTM D256

Hardness

	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	86	86	ASTM D785

Thermal

	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	257 °F	125 °C	
264 Psi (1.8 Mpa), Unannealed	171 °F	77.0 °C	

Additional Information

Ash Content, ASTM D2584: 30%

Notes

These are typical property values not to be construed as specification limits.