

Technical Data Sheet

# Ferrex GPP40CA04NA

Polypropylene Homopolymer  
LyondellBasell Industries  
Engineering Plastics

General			
Filler / Reinforcement	• Calcium Carbonate, 40% Filler by Weight		
Features	• High Gloss	• Homopolymer	
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.25	1.25 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	1.5 g/10 min	1.5 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	3800 psi	26.2 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	40 %	40 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	345000 psi	2380 MPa	
Tangent : 73°F (23°C)	408000 psi	2810 MPa	
Flexural Strength (Yield, 73°F (23°C))	6500 psi	44.8 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.4 ft·lb/in	75 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	18 ft·lb/in	960 J/m	ASTM D4812
Gardner Impact	210 in·lb	23.7 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	235 °F	113 °C	
264 Psi (1.8 Mpa), Unannealed	160 °F	71.1 °C	

Additional Information			
Filler Content, ASTM D2584: 42%			

**Notes**

These are typical property values not to be construed as specification limits.