

Technical Data Sheet

# Ferro Pp CPP30GF15NA

Polypropylene Homopolymer  
LyondellBasell Industries  
Engineering Plastics

General	
Filler / Reinforcement	• Mineral, 32% Filler by Weight
Features	• Homopolymer
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.16	1.16 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	22 g/10 min	22 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	4100 psi	28.3 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	15 %	15 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	341000 psi	2350 MPa	
Tangent : 73°F (23°C)	426000 psi	2940 MPa	
Flexural Strength (73°F (23°C))	6900 psi	47.6 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.50 ft·lb/in	27 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	7.6 ft·lb/in	410 J/m	ASTM D4812
Gardner Impact	15.0 in·lb	1.69 J	ASTM D5420

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore D)	74	74	ASTM D2240

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	245 °F	118 °C	
264 Psi (1.8 Mpa), Unannealed	150 °F	65.6 °C	

Technical Data Sheet

**Ferro Pp CPP30GF15NA**

Polypropylene Homopolymer  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Rear Temperature	395 to 400 °F	202 to 204 °C
Middle Temperature	400 to 410 °F	204 to 210 °C
Front Temperature	410 to 415 °F	210 to 213 °C
Nozzle Temperature	415 to 425 °F	213 to 218 °C
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Back Pressure	50.0 to 100 psi	0.345 to 0.689 MPa

**Notes**

These are typical property values not to be construed as specification limits.