

Technical Data Sheet

Ferro Pp LPP20BD39WH

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General	
Filler / Reinforcement	• Calcium Carbonate, 20% Filler by Weight
Features	• Homopolymer
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.06	1.06 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	14 g/10 min	14 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	4100 psi	28.3 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	45 %	45 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	246000 psi	1700 MPa	
Tangent : 73°F (23°C)	272000 psi	1880 MPa	
Flexural Strength (Yield, 73°F (23°C))	6000 psi	41.4 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.80 ft·lb/in	43 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	19 ft·lb/in	990 J/m	ASTM D4812
Gardner Impact	22.0 in·lb	2.49 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	235 °F	113 °C	
264 Psi (1.8 Mpa), Unannealed	145 °F	62.8 °C	

Additional Information
Filler Content, ASTM D2584: 22%

Technical Data Sheet

Ferro Pp LPP20BD39WH

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.