

Technical Data Sheet

# Ferro Pp LPP40BD23WH

Polypropylene Homopolymer  
LyondellBasell Industries  
Engineering Plastics

General	
Filler / Reinforcement	• Calcium Carbonate, 40% Filler by Weight
Features	• Homopolymer
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.26	1.26 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	13 g/10 min	13 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	3500 psi	24.1 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	22 %	22 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	344000 psi	2370 MPa	
Tangent : 73°F (23°C)	369000 psi	2540 MPa	
Flexural Strength (73°F (23°C))	6000 psi	41.4 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.40 ft·lb/in	21 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	7.8 ft·lb/in	420 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	32.0 in·lb	3.62 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	240 °F	116 °C	
264 Psi (1.8 Mpa), Unannealed	152 °F	66.7 °C	

Technical Data Sheet

**Ferro Pp LPP40BD23WH**

Polypropylene Homopolymer  
LyondellBasell Industries  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

**Notes**

These are typical property values not to be construed as specification limits.