

Technical Data Sheet

Ferro Pp NPP00GC11NA

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics

General	
Features	• Homopolymer
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.910	0.908 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	5.5 g/10 min	5.5 g/10 min	ASTM D1238
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	5200 psi	35.9 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	120 %	120 %	ASTM D638
Flexural Modulus - Tangent (73°F (23°C))	216000 psi	1490 MPa	ASTM D790
Flexural Strength (Yield, 73°F (23°C))	6500 psi	44.8 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.50 ft·lb/in	27 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	20 ft·lb/in	1100 J/m	ASTM D4812
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	208 °F	97.8 °C	
264 Psi (1.8 Mpa), Unannealed	167 °F	75.0 °C	

Technical Data Sheet

Ferro Pp NPP00GC11NA

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.