

Technical Data Sheet

# Ferro Pp NPP00GDV04WH

Polypropylene Homopolymer

LyondellBasell Industries

Engineering Plastics

**General**

- |                   |                     |
|-------------------|---------------------|
| Features          | • Homopolymer       |
| Processing Method | • Injection Molding |

**Physical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.930	0.928 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	1.4 g/10 min	1.4 g/10 min	ASTM D1238

**Mechanical**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	5100 psi	35.2 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	45 %	45 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	204000 psi	1410 MPa	
Tangent : 73°F (23°C)	205000 psi	1410 MPa	
Flexural Strength (73°F (23°C))	6700 psi	46.2 MPa	ASTM D790

**Impact**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.1 ft·lb/in	59 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	20 ft·lb/in	1100 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	15.0 in·lb	1.69 J	ASTM D5420

**Thermal**

	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	205 °F	96.1 °C	
264 Psi (1.8 Mpa), Unannealed	135 °F	57.2 °C	

Technical Data Sheet

**Ferro Pp NPP00GDV04WH**

Polypropylene Homopolymer  
 LyondellBasell Industries  
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

**Notes**

These are typical property values not to be construed as specification limits.