

Technical Data Sheet

Ferro Pp TPP20AD59HB-NA

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General		
Filler / Reinforcement	• Talc, 24% Filler by Weight	
Features	• General Purpose	• Homopolymer
Appearance	• Natural Color	
Forms	• Pellets	
Processing Method	• Injection Molding	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.07	1.07 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	7.5 g/10 min	7.5 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (73°F (23°C))	4800 psi	33.1 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	25 %	25 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	350000 psi	2410 MPa	
Tangent : 73°F (23°C)	404000 psi	2790 MPa	
Flexural Strength (73°F (23°C))	7700 psi	53.1 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.50 ft·lb/in	27 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	11 ft·lb/in	570 J/m	ASTM D4812
Gardner Impact (73°F (23°C))	6.50 in·lb	0.734 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	260 °F	127 °C	
264 Psi (1.8 Mpa), Unannealed	160 °F	71.1 °C	

Technical Data Sheet

Ferro Pp TPP20AD59HB-NA

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Rear Temperature	400 to 410 °F	204 to 210 °C
Middle Temperature	410 to 415 °F	210 to 213 °C
Front Temperature	415 to 420 °F	213 to 216 °C
Nozzle Temperature	420 to 425 °F	216 to 218 °C
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Screw Speed	100 to 150 rpm	100 to 150 rpm
Clamp Tonnage	2.0 to 3.0 tons/in ²	2.8 to 4.1 kN/cm ²
Screw L/D Ratio	20.0:1.0	20.0:1.0
Screw Compression Ratio	2.0:1.0	2.0:1.0

Notes

These are typical property values not to be construed as specification limits.