

Technical Data Sheet

Ferro Pp TPP20AF20BK

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics

Product Description

25% minimum post consumer recycle (P.C.R.)
 Meets/Exceeds Ford Engineering Specification WSH-M4D293-B2.
 Primary end use is for AC/heater housings.

General

Filler / Reinforcement	• Talc, 21% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Stabilized • Homopolymer
Automotive Specifications	• FORD WSH-M4D293-B2 Color: N • VISTEON VAM-PP010000-T20BKH25 Application 003
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.06 g/cm ³	1.06 g/cm ³	ISO 1183/A
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	10 g/10 min	10 g/10 min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Stress (Yield, 73°F (23°C))	4370 psi	30.1 MPa	ISO 527-2
Flexural Modulus	348000 psi	2400 MPa	ISO 178
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact Strength			ISO 180
-40°F (-40°C)	1.1 ft·lb/in ²	2.4 kJ/m ²	
73°F (23°C)	1.7 ft·lb/in ²	3.6 kJ/m ²	
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	244 °F	118 °C	ISO 75-2/B
264 Psi (1.8 Mpa), Unannealed	156 °F	69.0 °C	ISO 75-2/A

Additional Information

Tensile/Izod Change, ISO 188, 1000 hours, 140°C: +5%/+5%

Technical Data Sheet

Ferro Pp TPP20AF20BK

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

Notes

These are typical property values not to be construed as specification limits.