

Technical Data Sheet

# Ferro Pp TPP20AF64UL

Polypropylene Homopolymer  
LyondellBasell Industries  
Engineering Plastics

General	
Filler / Reinforcement	• Talc, 20% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Stabilized • Homopolymer
Appearance	• Grey
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.09	1.09 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	5.5 g/10 min	5.5 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	4900 psi	33.8 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	15 %	15 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	351000 psi	2420 MPa	
Tangent : 73°F (23°C)	391000 psi	2700 MPa	
Flexural Strength (Yield, 73°F (23°C))	7700 psi	53.1 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	0.70 ft-lb/in	37 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	8.1 ft-lb/in	430 J/m	ASTM D4812
Gardner Impact	6.00 in-lb	0.678 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	255 °F	124 °C	
264 Psi (1.8 Mpa), Unannealed	160 °F	71.1 °C	

Additional Information
Filler Content, ASTM D2584: 21%

Technical Data Sheet

# Ferro Pp TPP20AF64UL

Polypropylene Homopolymer  
 LyondellBasell Industries  
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C

**Notes**

These are typical property values not to be construed as specification limits.