

Technical Data Sheet

Fiberfil J-60/30

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

General	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Homopolymer
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.12	1.12 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Water Absorption (24 Hr)	0.030 %	0.030 %	ASTM D570

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus (73°F (23°C))	850000 psi	5860 MPa	ASTM D638
Tensile Strength (73°F (23°C))	9500 psi	65.5 MPa	ASTM D638
Tensile Elongation (Yield, 73°F (23°C))	3.0 %	3.0 %	ASTM D638
Flexural Modulus - Tangent (73°F (23°C))	700000 psi	4830 MPa	ASTM D790
Flexural Strength (73°F (23°C))	15000 psi	103 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
73°F (23°C), 0.125 In (3.18 Mm)	1.3 ft-lb/in	69 J/m	

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Rockwell Hardness (R-scale)	105	105	ASTM D785

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	315 °F	157 °C	
264 Psi (1.8 Mpa), Unannealed	300 °F	149 °C	

Additional Information
Rockwell Hardness, ASTM D785, R-Scale: 100 to 110

Notes

These are typical property values not to be construed as specification limits.