

Technical Data Sheet

Gapex Hp RPP30EC16BK

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics

General			
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight		
Features	• Chemically Coupled	• Homopolymer	
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.12	1.12 g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	6.5 g/10 min	6.5 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	11800 psi	81.4 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	4.0 %	4.0 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	729000 psi	5020 MPa	
Tangent : 73°F (23°C)	774000 psi	5340 MPa	
Flexural Strength (Yield, 73°F (23°C))	18200 psi	125 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	2.0 ft·lb/in	110 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	12 ft·lb/in	620 J/m	ASTM D4812
Gardner Impact	4.50 in·lb	0.508 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 Psi (0.45 Mpa), Unannealed	320 °F	160 °C	
264 Psi (1.8 Mpa), Unannealed	300 °F	149 °C	

Additional Information			
Filler Content, ASTM D2584: 30%			

Technical Data Sheet

Gapex Hp RPP30EC16BK

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	430 to 460 °F	221 to 238 °C
Middle Temperature	440 to 470 °F	227 to 243 °C
Front Temperature	450 to 500 °F	232 to 260 °C
Nozzle Temperature	450 to 500 °F	232 to 260 °C
Processing (Melt) Temp	430 to 460 °F	221 to 238 °C
Mold Temperature	100 to 150 °F	38 to 66 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Cushion	0.200 to 0.500 in	5.08 to 12.7 mm

Notes

These are typical property values not to be construed as specification limits.