

Technical Data Sheet

**GAPEX<sup>®</sup>**  
**HP RPP10EB90AL**

Polypropylene Homopolymer  
 Engineering Plastics



General			
Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Chemically Coupled	• Heat Stabilized	• Homopolymer
Forms	• Pellets		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.10	1.10 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.5 g/10 min	6.5 g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	9.0E-3 in/in	0.90 %	
Across Flow	0.013 in/in	1.3 %	

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	6900 psi	47.6 MPa	ASTM D638
Tensile Elongation (Break, 73°F (23°C))	4.5 %	4.5 %	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F (23°C)	377000 psi	2600 MPa	
Tangent : 73°F (23°C)	390000 psi	2690 MPa	
Flexural Strength (Yield, 73°F (23°C))	11000 psi	75.8 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (73°F (23°C))	1.1 ft·lb/in	59 J/m	ASTM D256
Unnotched Izod Impact (73°F (23°C))	7.5 ft·lb/in	400 J/m	ASTM D256
Gardner Impact	3.50 in·lb	0.395 J	ASTM D5420

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	305 °F	152 °C	
264 psi (1.8 MPa), Unannealed	255 °F	124 °C	


Additional Information			
Filler Content, ASTM D2584: 13%			

Technical Data Sheet

**GAPEX®**

**HP RPP10EB90AL**

Polypropylene Homopolymer  
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	160 to 180 °F	71 to 82 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	430 to 460 °F	221 to 238 °C
Middle Temperature	440 to 470 °F	227 to 243 °C
Front Temperature	450 to 500 °F	232 to 260 °C
Nozzle Temperature	450 to 500 °F	232 to 260 °C
Processing (Melt) Temp	430 to 460 °F	221 to 238 °C
Mold Temperature	100 to 150 °F	38 to 66 °C
Injection Rate	Slow-Moderate	Slow-Moderate
Back Pressure	20.0 to 50.0 psi	0.138 to 0.345 MPa
Cushion	0.200 to 0.500 in	5.08 to 12.7 mm

**Notes**

These are typical property values not to be construed as specification limits.