

Technical Data Sheet

Hostacom FPP 30 GFC

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

Product Description

30% glass fiber reinforced PP-Homopolymer chemically coupled
Former name: Polyfort FPP 30 GFC

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Chemically Coupled • Homopolymer
UL File Number	• E86615
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Density	1.13 g/cm ³	1.13 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 Kg)	5.0 cm ³ /10min	5.0 cm ³ /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Tensile Modulus	943000 psi	6500 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	12200 psi	84.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.8 %	2.8 %	ISO 527-2/1A/5
Flexural Modulus ¹	870000 psi	6000 MPa	ISO 178
Flexural Stress ¹			ISO 178
3.4% Strain	18600 psi	128 MPa	
3.6% Strain ²	18300 psi	126 MPa	

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
--------	-------------------------	--------------------	-------------

Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	3.8 ft·lb/in ²	8.0 kJ/m ²	
73°F (23°C)	4.8 ft·lb/in ²	10 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	21 ft·lb/in ²	45 kJ/m ²	
73°F (23°C)	23 ft·lb/in ²	48 kJ/m ²	

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
----------	-------------------------	--------------------	-------------

Ball Indentation Hardness (H 358/30)	17400 psi	120 MPa	ISO 2039-1
--------------------------------------	-----------	---------	------------

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
---------	-------------------------	--------------------	-------------

Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	318 °F	159 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	320 °F	160 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	266 °F	130 °C	ISO 306/B50
--	329 °F	165 °C	ISO 306/A50
Ball Pressure Test (293°F (145°C))	Pass	Pass	IEC 60695-10-2

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
------------	-------------------------	--------------------	-------------

Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1

Technical Data Sheet

Hostacom FPP 30 GFC

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	2.3 in/min	58 mm/min	ISO 3795
0.0787 In (2.00 Mm)	2.3 in/min	58 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1430 °F	775 °C	
0.12 In (3.0 Mm)	1430 °F	775 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1470 °F	800 °C	
0.12 In (3.0 Mm)	1470 °F	800 °C	

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Simulation data (also for Crash simulation) is available on special request

Technical Data Sheet

Hostacom FPP 30 GFC

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Moderate-Fast	Moderate-Fast

Injection Notes

Polypropylene is not hygroscopic and generally does not require drying. As a good practice and to avoid residual humidity from transport or storage conditions, we recommend drying the material.

Ensure good mold venting

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Technical Data Sheet



Hostacom FPP 30 GFC

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

Notes

¹ 0.079 in/min (2.0 mm/min)

² at Break

Notes

These are typical property values not to be construed as specification limits.