

**Technical Data Sheet**  
**Lucent PP CPP-120**  
 Polypropylene Homopolymer  
 Engineering Plastics



**Product Description**

20% Calcium Carbonate Filled, Homopolymer Polypropylene

Melt Flow Adjustable for Application  
 Colors Available  
 Add "U" for UV Stabilized  
 Add "H" for Heat Stabilized

**General**

- |                        |                                           |
|------------------------|-------------------------------------------|
| Filler / Reinforcement | • Calcium Carbonate, 20% Filler by Weight |
| Features               | • Homopolymer                             |
| Appearance             | • Colors Available                        |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.05	1.05 g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	0.012 in/in	1.2 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	4000 psi	27.6 MPa	ASTM D638
Tensile Elongation (Break)	> 10 %	> 10 %	ASTM D638
Flexural Modulus	280000 psi	1930 MPa	ASTM D790
Flexural Strength	6500 psi	44.8 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 in (3.18 mm))	0.80 ft-lb/in	43 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	145 °F	62.8 °C	ASTM D648

**Notes**

These are typical property values not to be construed as specification limits.