

**Technical Data Sheet**  
**Lucent PP CPP-130**  
 Polypropylene Homopolymer  
 Engineering Plastics



**Product Description**

30% Calcium Carbonate Filled, Homopolymer Polypropylene

- Melt Flow Adjustable for Application
- Colors Available
- Add "U" for UV Stabilized
- Add "H" for Heat Stabilized

**General**

- Filler / Reinforcement • Calcium Carbonate, 30% Filler by Weight
- Features • Homopolymer
- Appearance • Colors Available

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.14	1.14 g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	0.012 in/in	1.2 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	3800 psi	26.2 MPa	ASTM D638
Tensile Elongation (Break)	> 10 %	> 10 %	ASTM D638
Flexural Modulus	350000 psi	2410 MPa	ASTM D790
Flexural Strength	6300 psi	43.4 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 in (3.18 mm))	0.80 ft-lb/in	43 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	155 °F	68.3 °C	ASTM D648

**Notes**

These are typical property values not to be construed as specification limits.