

**Technical Data Sheet**  
**Lucent PP GPP-110**  
 Polypropylene Homopolymer  
 Engineering Plastics



**Product Description**

10% Glass Fiber Reinforced, Chemically Coupled, Homopolymer Polypropylene

Melt Flow Adjustable for Application  
 Colors Available  
 Add "U" for UV Stabilized  
 Add "H" for Heat Stabilized

**General**

Filler / Reinforcement	• Glass Fiber, 10% Filler by Weight		
Features	• Chemically Coupled	• Homopolymer	
Appearance	• Colors Available		

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	0.980	0.978 g/cm <sup>3</sup>	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	8.0E-3 in/in	0.80 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	6700 psi	46.2 MPa	ASTM D638
Tensile Elongation (Break)	7.0 %	7.0 %	ASTM D638
Flexural Modulus	325000 psi	2240 MPa	ASTM D790
Flexural Strength	9300 psi	64.1 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 in (3.18 mm))	0.80 ft·lb/in	43 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	235 °F	113 °C	ASTM D648

**Notes**

These are typical property values not to be construed as specification limits.