



Technical Data Sheet

Lucent Pp TPP-0130

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics

Product Description

30% Talc Filled, Homopolymer Polypropylene

Melt Flow Adjustable for Application
 Colors Available
 Add "U" for UV Stabilized
 Add "H" for Heat Stabilized

General

- | | |
|------------------------|------------------------------|
| Filler / Reinforcement | • Talc, 30% Filler by Weight |
| Features | • Homopolymer |
| Appearance | • Colors Available |
| Processing Method | • Injection Molding |

| Physical | Nominal Value (English) | Nominal Value (SI) | Test Method |
|--|-------------------------|------------------------|-------------|
| Density / Specific Gravity | 1.14 | 1.14 g/cm ³ | ASTM D792 |
| Mechanical | Nominal Value (English) | Nominal Value (SI) | Test Method |
| Tensile Strength (Yield) | 4600 psi | 31.7 MPa | ASTM D638 |
| Tensile Elongation (Break) | > 10 % | > 10 % | ASTM D638 |
| Flexural Modulus | 440000 psi | 3030 MPa | ASTM D790 |
| Flexural Strength | 7600 psi | 52.4 MPa | ASTM D790 |
| Impact | Nominal Value (English) | Nominal Value (SI) | Test Method |
| Notched Izod Impact (0.125 In (3.18 Mm)) | 0.50 ft·lb/in | 27 J/m | ASTM D256 |
| Thermal | Nominal Value (English) | Nominal Value (SI) | Test Method |
| Deflection Temperature Under Load 264 Psi (1.8 Mpa), Unannealed | 175 °F | 79.4 °C | ASTM D648 |

Technical Data Sheet

Lucent Pp TPP-0130

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics



| Injection | Nominal Value (English) | Nominal Value (SI) |
|------------------------|-------------------------|--------------------|
| Drying Temperature | 176 °F | 80 °C |
| Drying Time | 2.0 to 3.0 hr | 2.0 to 3.0 hr |
| Processing (Melt) Temp | 428 to 500 °F | 220 to 260 °C |
| Mold Temperature | 86 to 140 °F | 30 to 60 °C |

Notes

These are typical property values not to be construed as specification limits.