

Technical Data Sheet

# Matrixx FPP1A30HC

Polypropylene Homopolymer  
 LyondellBasell Industries  
 Engineering Plastics

**Product Description**

FPP1A30HC is a 30% Glass-Filled Polypropylene Homopolymer

**General**

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Homopolymer
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 Kg)	4.9 g/10 min	4.9 g/10 min	ASTM D1238

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield, 73°F (23°C))	12900 psi	88.8 MPa	ASTM D638
Flexural Modulus - Tangent 73°F (23°C), 0.125 In (3.18 Mm)	901000 psi	6220 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact 73°F (23°C), 0.125 In (3.18 Mm)	1.8 ft-lb/in	96 J/m	ASTM D256

Technical Data Sheet

# Matrixx FPP1A30HC

Polypropylene Homopolymer  
 LyondellBasell Industries  
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	180 to 220 °F	82 to 104 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	390 to 470 °F	199 to 243 °C
Middle Temperature	390 to 470 °F	199 to 243 °C
Front Temperature	390 to 470 °F	199 to 243 °C
Processing (Melt) Temp	390 to 470 °F	199 to 243 °C
Mold Temperature	60 to 150 °F	16 to 66 °C
Injection Rate	Moderate	Moderate
Back Pressure	< 50.0 psi	< 0.345 MPa
Screw Speed	20 to 60 rpm	20 to 60 rpm
Cushion	0.250 to 0.500 in	6.35 to 12.7 mm

**Injection Notes**  
 Drying not normally required

**Notes**

These are typical property values not to be construed as specification limits.