



Moplen HP509N

Polypropylene, Homopolymer

Product Description

Moplen HP509N is a homopolymer used for general purpose injection moulding applications. It exhibits good flow and stiffness.

Moplen HP509N is suitable for food contact.

Product Characteristics

Test Method used ISO

Typical Properties	Method	Value	Unit
Physical			
Density	ISO 1183	0.9	g/cm ³
Melt flow rate (MFR) (230°C/2.16kg)	ISO 1133	12	g/10 min
Melt volume flow rate (230°C/2.16kg)	ISO 1133	16	cm ³ /10min
Mechanical			
Tensile Modulus	ISO 527-1, -2	1550	MPa
Tensile Stress at Yield	ISO 527-1, -2	35	MPa
Tensile Strain at Break	ISO 527-1, -2	>50	%
Tensile Strain at Yield	ISO 527-1, -2	10	%
Impact			
Charpy unnotched impact strength (23 °C, Type 1, Edgewise)	ISO 179	110	kJ/m ²
(0 °C, Type 1, Edgewise)		30	
Charpy notched impact strength (23 °C, Type 1, Edgewise, Notch A)	ISO 179	3	kJ/m ²
Thermal			
Heat deflection temperature B (0.45 MPa) Unannealed	ISO 75B-1, -2	95	°C
Vicat softening temperature A/50	ISO 306	153	°C
Vicat softening temperature B/50	ISO 306	85	°C