

Technical Data Sheet

Polyflam RPP 3225 CS1

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics

Product Description

25% glass fibre reinforced flame retardant PP homo polymer compound; without PBDE

General

Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight
Features	• Copper Contact Stabilized • High Strength • Flame Retardant • Homopolymer
UL File Number	• E86615
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PP GF25 FR(17)

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.48 g/cm ³	1.48 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 Kg)	5.0 cm ³ /10min	5.0 cm ³ /10min	ISO 1133
Water Absorption Equilibrium, 73°F (23°C), 50% Rh	0.16 %	0.16 %	ISO 62

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.15E+6 psi	7900 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	12000 psi	83.0 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0 %	3.0 %	ISO 527-2/1A/5

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength -22°F (-30°C)	4.3 ft·lb/in ²	9.0 kJ/m ²	ISO 179/1eA
73°F (23°C)	4.8 ft·lb/in ²	10 kJ/m ²	
Charpy Unnotched Impact Strength -22°F (-30°C)	19 ft·lb/in ²	39 kJ/m ²	ISO 179/1eU
73°F (23°C)	19 ft·lb/in ²	40 kJ/m ²	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 66 Psi (0.45 Mpa), Unannealed	315 °F	157 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	293 °F	145 °C	ISO 75-2/Af
Vicat Softening Temperature --	264 °F	129 °C	ISO 306/B50
--	322 °F	161 °C	ISO 306/A50
Ball Pressure Test (293°F (145°C))	Pass	Pass	IEC 60695-10-2
RTI Elec			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	
RTI Imp			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	
RTI Str			UL 746B
0.06 In (1.5 Mm)	149 °F	65.0 °C	
0.12 In (3.0 Mm)	149 °F	65.0 °C	

Technical Data Sheet

Polyflam RPP 3225 CS1


Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Comparative Tracking Index	600 V	600 V	IEC 60112
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			ISO 3795
0.0591 In (1.50 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	
0.118 In (3.00 Mm), Self-extinguishing	0.0 in/min	0.0 mm/min	
Flame Rating			UL 94 IEC 60695-11-10, -20
0.06 In (1.5 Mm)	V-0	V-0	
0.12 In (3.0 Mm)	V-0	V-0	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 In (1.5 Mm)	1760 °F	960 °C	
0.12 In (3.0 Mm)	1760 °F	960 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 In (1.5 Mm)	1290 °F	700 °C	
0.12 In (3.0 Mm)	1430 °F	775 °C	
Oxygen Index	28 %	28 %	ISO 4589-2

Technical Data Sheet

Polyflam RPP 3225 CS1

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	158 to 176 °F	70 to 80 °C
Drying Time	2.0 to 4.0 hr	2.0 to 4.0 hr
Rear Temperature	356 °F	180 °C
Middle Temperature	392 °F	200 °C
Front Temperature	410 °F	210 °C
Nozzle Temperature	428 °F	220 °C
Processing (Melt) Temp	356 to 428 °F	180 to 220 °C
Mold Temperature	104 to 176 °F	40 to 80 °C
Injection Pressure	11600 to 17400 psi	80.0 to 120 MPa
Injection Rate	Slow-Moderate	Slow-Moderate
Holding Pressure	5800 to 13100 psi	40.0 to 90.0 MPa
Back Pressure	725 to 1450 psi	5.00 to 10.0 MPa
Cushion	< 0.197 in	< 5.00 mm
Screw Speed	< 709 in/min	< 18 m/min

Injection Notes

Mould surface contacting melt should be of non-corrosive steel (content of chrome > 12%)

Notes

These are typical property values not to be construed as specification limits.