

Technical Data Sheet

# Polyfort FPP 20 GFM HI

Polypropylene Homopolymer  
LyondellBasell Industries  
Engineering Plastics

**Product Description**

20% grinded glass fibre reinforced impact modified PP-Homopolymer

**General**

- |                        |  |
|------------------------|--|
| Filler / Reinforcement | • Milled Glass Fiber, 20% Filler by Weight |
| Processing Method      | • Injection Molding                        |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.04 g/cm <sup>3</sup>	1.04 g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°c/2.16 Kg)	3.5 cm <sup>3</sup> /10min	3.5 cm <sup>3</sup> /10min	ISO 1133
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	406000 psi	2800 MPa	ISO 527-1/1A/1
Tensile Stress (Yield)	5080 psi	35.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	7.0 %	7.0 %	ISO 527-2/1A/50
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°f (-30°c)	0.95 ft·lb/in <sup>2</sup>	2.0 kJ/m <sup>2</sup>	
73°f (23°c)	1.9 ft·lb/in <sup>2</sup>	4.0 kJ/m <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°f (-30°c)	7.1 ft·lb/in <sup>2</sup>	15 kJ/m <sup>2</sup>	
73°f (23°c)	18 ft·lb/in <sup>2</sup>	38 kJ/m <sup>2</sup>	
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	11700 psi	81.0 MPa	ISO 2039-1
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	230 °F	110 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	158 °F	70.0 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	196 °F	91.0 °C	ISO 306/B50
--	307 °F	153 °C	ISO 306/A50
Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1
Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	

**Additional Information**

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

# Polyfort FPP 20 GFM HI

Polypropylene Homopolymer  
 LyondellBasell Industries  
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Moderate-Fast	Moderate-Fast

### Injection Notes

Polypropylene is not hygroscopic and generally does not require drying. As a good practice and to avoid residual humidity from transport or storage conditions, we recommend drying the material.

Ensure good mold venting

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

### Notes

These are typical property values not to be construed as specification limits.