

Technical Data Sheet
POLYFORT® FPP 20 T
 Polypropylene Homopolymer
 Engineering Plastics



Product Description

20% talc filled PP-Homopolymer

General

Filler / Reinforcement	• Talc, 20% Filler by Weight
UL File Number	• E86615
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PP-T

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.06 g/cm ³	1.06 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	9.00 cm ³ /10min	9.00 cm ³ /10min	ISO 1133
Molding Shrinkage	0.90 to 1.3 %	0.90 to 1.3 %	ISO 294-4

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	377000 psi	2600 MPa	ISO 527-2/1A/1
Tensile Stress (Yield)	4790 psi	33.0 MPa	ISO 527-2/1A/50
Tensile Strain (Yield)	6.0 %	6.0 %	ISO 527-2/1A/50

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	0.95 ft·lb/in ²	2.0 kJ/m ²	
73°F (23°C)	1.4 ft·lb/in ²	3.0 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	6.7 ft·lb/in ²	14 kJ/m ²	
73°F (23°C)	18 ft·lb/in ²	38 kJ/m ²	

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	11900 psi	82.0 MPa	ISO 2039-1

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Heat Deflection Temperature			
66 psi (0.45 MPa), Unannealed	228 °F	109 °C	ISO 75-2/Bf
264 psi (1.8 MPa), Unannealed	136 °F	58.0 °C	ISO 75-2/ Af
Vicat Softening Temperature			
--	306 °F	152 °C	ISO 306/A50
--	183 °F	84.0 °C	ISO 306/B50
Ball Pressure Test (257°F (125°C))	Pass	Pass	IEC 60695-10-2

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 in (2.00 mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in (1.5 mm)	HB	HB	
0.12 in (3.0 mm)	HB	HB	
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in (1.5 mm)	1340 °F	725 °C	
0.12 in (3.0 mm)	1430 °F	775 °C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in (1.5 mm)	1380 °F	750 °C	
0.12 in (3.0 mm)	1470 °F	800 °C	

Technical Data Sheet

POLYFORT[®] FPP 20 T

Polypropylene Homopolymer

Engineering Plastics



Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

POLYFORT® FPP 20 T

Polypropylene Homopolymer
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Suggested Max Regrind	20 %	20 %
Processing (Melt) Temp	446 to 518 °F	230 to 270 °C
Mold Temperature	104 to 158 °F	40 to 70 °C

Injection Notes

Drying normally not necessary.

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

These are typical property values not to be construed as specification limits.