

Technical Data Sheet

Polyfort FPP 40 GFC LE K2097

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

Product Description
40 % glass fibre reinforced PP homopolymer, long term heat stabilized, low emission

General		
Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight	
Features	• Chemically Coupled • Heat Stabilized	• Homopolymer • Low Emissions
Processing Method	• Injection Molding	
Resin ID (ISO 1043)	• PP-H 40 GF	

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density	1.21 g/cm ³	1.21 g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 Kg)	4.0 cm ³ /10min	4.0 cm ³ /10min	ISO 1133

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Modulus	1.31E+6 psi	9000 MPa	ISO 527-1/1A/1
Tensile Stress (Break)	14500 psi	100 MPa	ISO 527-2/1A/5
Tensile Strain (Break)	2.8 %	2.8 %	ISO 527-2/1A/5
Flexural Modulus	1.20E+6 psi	8300 MPa	ISO 178
Flexural Stress ¹			ISO 178
3.1% Strain	21000 psi	145 MPa	
3.3% Strain	18900 psi	130 MPa	

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F (-30°C)	3.8 ft·lb/in ²	8.0 kJ/m ²	
73°F (23°C)	4.8 ft·lb/in ²	10 kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F (-30°C)	23 ft·lb/in ²	49 kJ/m ²	
73°F (23°C)	24 ft·lb/in ²	50 kJ/m ²	

Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Ball Indentation Hardness (H 358/30)	22200 psi	153 MPa	ISO 2039-1

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			
66 Psi (0.45 Mpa), Unannealed	318 °F	159 °C	ISO 75-2/Bf
264 Psi (1.8 Mpa), Unannealed	293 °F	145 °C	ISO 75-2/Af
Vicat Softening Temperature			
--	275 °F	135 °C	ISO 306/B50
--	329 °F	165 °C	ISO 306/A50

Electrical	Nominal Value (English)	Nominal Value (SI)	Test Method
Surface Resistivity	> 1.0E+15 ohms	> 1.0E+15 ohms	IEC 60093
Volume Resistivity	> 1.0E+13 ohms·m	> 1.0E+13 ohms·m	IEC 62631-3-1

Flammability	Nominal Value (English)	Nominal Value (SI)	Test Method
Burning Rate			
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	ISO 3795
0.0787 In (2.00 Mm)	< 3.9 in/min	< 100 mm/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 In (1.5 Mm)	HB	HB	
0.12 In (3.0 Mm)	HB	HB	

Technical Data Sheet



Polyfort FPP 40 GFC LE K2097

Polypropylene Homopolymer
LyondellBasell Industries
Engineering Plastics

Additional Information

- 1.) Not for use in food contact applications
- 2.) Not for use in medical or pharmaceutical applications

Technical Data Sheet

Polyfort FPP 40 GFC LE K2097

Polypropylene Homopolymer
 LyondellBasell Industries
 Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	176 °F	80 °C
Drying Time	2.0 to 3.0 hr	2.0 to 3.0 hr
Processing (Melt) Temp	428 to 500 °F	220 to 260 °C
Mold Temperature	86 to 140 °F	30 to 60 °C
Injection Rate	Moderate-Fast	Moderate-Fast

Injection Notes

Polypropylene is not hygroscopic and generally does not require drying. As a good practice and to avoid residual humidity from transport or storage conditions, we recommend drying the material.

Ensure good mold venting

Injection molding parameters also influence emission properties, which are often required for automotive interior applications. Generally speaking, the emission, odor and fogging behavior of finished parts is improved by lowering the melt temperature, reducing residence time and avoiding high shear stress.

Notes

¹ 0.079 in/min (2.0 mm/min)

Notes

These are typical property values not to be construed as specification limits.