

Technical Data Sheet

**Polyflam PP-60/V2 NATLNAT**



Polypropylene, Homopolymer

**Product Description**

Polyflam PP-60/V2 NATLNAT is a Polypropylene Homopolymer material. Features include: Homopolymer.

<b>Attribute</b>	Homopolymer
<b>Forms</b>	Pellets
<b>Additive</b>	Flame Retardant

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	7.0	g/10 min	ASTM D1238
Density - Specific Gravity	0.958	g/cm <sup>3</sup>	ASTM D792
<b>Mechanical</b>			
Tensile Strength, (23 °C)	37.9	MPa	ASTM D638
Tensile Elongation at Yield, (23 °C)	15	%	ASTM D638
Flexural Modulus, (23 °C, Tangent)	1480	MPa	ASTM D790
Tensile Modulus, (23 °C)	1550	MPa	ASTM D638
Flexural Strength, (23 °C)	42.1	MPa	ASTM D790
<b>Impact</b>			
Notched Izod Impact, (23 °C, 3.18 mm)	48	J/m	ASTM D256
<b>Hardness</b>			
Rockwell Hardness, (R-Scale)	90 to 95		ASTM D785
<b>Thermal</b>			
Deflection Temperature Under Load Unannealed (264 psi)	76.7	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi)	82.2	°C	ASTM D648
<b>Additional Information</b>			
Water Absorption at 24 hrs	0.02	%	ASTM D570
<b>UL Information</b>			
Flame Rating, (1.5 mm)	V-2		UL 94

Injection Parameters	Nominal Value	Units
Drying Time	2	hr
Drying Temperature	77	°C
Suggested Max Moisture	0.2	%
Nozzle Temperature	182 to 193	°C
Processing (Melt) Temp	193 to 216	°C
Front Temperature	188 to 204	°C
Middle Temperature	193 to 210	°C
Rear Temperature	182 to 199	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 0.689	MPa
Mold Temperature	32 to 71	°C