

Technical Data Sheet

Polyfort APP30GM06NA-NA GAPEXNAT



Polypropylene, Homopolymer

Product Description

Gapex APP30GM06NA is a 30% Glass & Talc Filled, UV Stabilized, Impact-Modified Polypropylene

| | |
|-----------------------------|-----------------------|
| Attribute | Homopolymer |
| Forms | Pellets |
| Appearance | Natural Color |
| Filler/Reinforcement | Glass Fiber\Talc, 30% |

| Typical Properties | Nominal Value | Units | Test Method |
|------------------------------------|----------------------|--------------|--------------------|
| Physical | | | |
| Melt Flow Rate, (230 °C/2.16 kg) | 8.7 | g/10 min | ASTM D1238 |
| Mechanical | | | |
| Tensile Strength at Yield | 44 | MPa | ASTM D638 |
| Flexural Modulus, (23 °C, Tangent) | 3650 | MPa | ASTM D790 |
| Impact | | | |
| Notched Izod Impact | 91 | J/m | ASTM D256 |