

Technical Data Sheet

Polyfort APP40GR22HB-BK GAPEXBLK



Polypropylene, Homopolymer

Product Description

Polyfort APP40GR22HB-BK GAPEXBLK is a Polypropylene Homopolymer Glass Fiber\Mineral, 40% filled material. Features include: Chemically Coupled.

Attribute	Chemically Coupled
Forms	Pellets
Appearance	Black
Filler/Reinforcement	Glass Fiber\Mineral, 40%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	4.0	g/10 min	ASTM D1238
Density - Specific Gravity	1.26	g/cm ³	ASTM D792
Mechanical			
Tensile Strength, (23 °C)	51.7	MPa	ASTM D638
Flexural Modulus			
(23 °C, 1% Secant)	4520	MPa	ASTM D790
(23 °C, Tangent)	5310	MPa	ASTM D790
Tensile Elongation at Break, (23 °C)	3.5	%	ASTM D638
Flexural Strength, (23 °C)	86.9	MPa	ASTM D790
Impact			
Gardner Impact, (23 °C)	0.282	J	ASTM D5420
Unnotched Izod Impact, (23 °C)	290	J/m	ASTM D4812
Notched Izod Impact, (23 °C)	53	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	141	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi)	157	°C	ASTM D648