

Technical Data Sheet

Polyfort RPP20EA34NA-NA GAPEXNAT



Polypropylene, Homopolymer

Product Description

Polyfort RPP20EA34NA-NA GAPEXNAT is a Polypropylene Homopolymer Glass Fiber, 20% filled material. Features include: Chemically Coupled, Heat Stabilized, and Homopolymer.

Attribute	Chemically Coupled; Heat Stabilized; Homopolymer
Forms	Pellets
Additive	Heat Stabilizer
Filler/Reinforcement	Glass Fiber, 20%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	5.0	g/10 min	ASTM D1238
Density - Specific Gravity	1.04	g/cm ³	ASTM D792
Mechanical			
Tensile Strength, (23 °C)	68.3	MPa	ASTM D638
Flexural Modulus			
(23 °C, 1% Secant)	3630	MPa	ASTM D790
(23 °C, Tangent)	3780	MPa	ASTM D790
Tensile Elongation at Break, (23 °C)	4.0	%	ASTM D638
Flexural Strength, (23 °C)	9.65	MPa	ASTM D790
Impact			
Gardner Impact	0.395	J	ASTM D5420
Unnotched Izod Impact, (23 °C)	440	J/m	ASTM D4812
Notched Izod Impact, (23 °C)	69	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	143	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi)	154	°C	ASTM D648

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 4.0	hr
Drying Temperature	71 to 82	°C
Nozzle Temperature	232 to 260	°C
Processing (Melt) Temp	221 to 238	°C
Front Temperature	232 to 260	°C
Middle Temperature	227 to 243	°C
Rear Temperature	221 to 238	°C
Injection Rate	Slow-Moderate	
Back Pressure	0.138 to 0.345	MPa
Mold Temperature	38 to 66	°C
Cushion	5.08 to 12.7	mm