

Technical Data Sheet

Polyfort TPP20AC15HB-BKBLK



Polypropylene, Homopolymer

Product Description

Polyfort TPP20AC15HB-BKBLK is a Polypropylene Homopolymer Talc, 20% filled material and is typically used in Injection Molding applications. Features include: Heat Stabilized, and Homopolymer.

Processing Method	Injection Molding
Attribute	Heat Stabilized; Homopolymer
Forms	Pellets
Appearance	Black
Additive	Heat Stabilizer
Application	Automotive Applications; General Purpose; Housings; Protective Coverings
Filler/Reinforcement	Talc, 20%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	5.5	g/10 min	ASTM D1238
Density - Specific Gravity	1.08	g/cm ³	ASTM D792
Mechanical			
Tensile Strength, (23 °C)	31.7	MPa	ASTM D638
Flexural Modulus			
(23 °C, 1% Secant)	2200	MPa	ASTM D790
(23 °C, Tangent)	2560	MPa	ASTM D790
Tensile Elongation at Break, (23 °C)	15	%	ASTM D638
Flexural Strength, (23 °C)	51.7	MPa	ASTM D790
Impact			
Gardner Impact, (23 °C)	0.678	J	ASTM D5420
Unnotched Izod Impact, (23 °C)	460	J/m	ASTM D4812
Notched Izod Impact, (23 °C)	32	J/m	ASTM D256
Hardness			
Rockwell Hardness, (R-Scale)	102		ASTM D785
Thermal			
Deflection Temperature Under Load Unannealed (264 psi)	69.4	°C	ASTM D648
Deflection Temperature Under Load Unannealed (66 psi)	121	°C	ASTM D648

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 3.0	hr
Drying Temperature	80	°C
Clamp Tonnage	2.8 to 4.1	kN/cm ²
Nozzle Temperature	216 to 218	°C
Screw Speed	100 to 150	rpm
Processing (Melt) Temp	220 to 260	°C
Front Temperature	213 to 216	°C
Screw L/D Ratio	20.0-1.0	
Screw Compression Ratio	2.0-1.0	
Middle Temperature	210 to 213	°C
Rear Temperature	204 to 210	°C
Back Pressure	0.138 to 0.345	MPa
Mold Temperature	30 to 60	°C