

Technical Data Sheet

Polyfort TPP40AJ35BK-BKBLK



Polypropylene, Homopolymer

Product Description

TPP40AJ35BK is 40% Talc-Filled Polypropylene Homopolymer

Processing Method	Injection Molding
Attribute	Heat Stabilized; Homopolymer
Forms	Pellets
Appearance	Black; Colors Available
Filler/Reinforcement	Talc, 40%

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	15	g/10 min	ISO 1133
Density	1.22	g/cm ³	ISO 1183
Mechanical			
Tensile Stress at Yield, (23 °C)	24.0	MPa	ISO 527-2
Flexural Modulus, (Chord)	3600	MPa	ISO 178
Impact			
Notched Izod Impact Strength, (23 °C)	2.0	kJ/m ²	ISO 180
Thermal			
Deflection Temperature Under Load Unannealed (0.45 MPa)	67	°C	ISO 75-2/B
Deflection Temperature Under Load Unannealed (1.80 MPa)	118	°C	ISO 75-2/A

Injection Parameters	Nominal Value	Units
Drying Time	2.0 to 3.0	hr
Drying Temperature	80	°C
Processing (Melt) Temp	220 to 260	°C
Mold Temperature	30 to 60	°C