

Technical Data Sheet

# Primefin V500/30GC

Polypropylene Homopolymer  
Engineering Plastics

**Product Description**

30% Glass Fiber Reinforced, Chemically Coupled, Homopolymer Polypropylene

Colors Available

Meets GMP.PP.009, GMP.PP.017

**General**

- |                        |   |
|------------------------|---|
| Filler / Reinforcement | • Glass Fiber, 30% Filler by Weight     |
| Features               | • Chemically Coupled      • Homopolymer |
| Appearance             | • Colors Available                      |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.13	1.13 g/cm <sup>3</sup>	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	4.0 g/10 min	4.0 g/10 min	ASTM D1238
Molding Shrinkage - Flow (0.125 in (3.18 mm))	3.0E-3 in/in	0.30 %	
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	11500 psi	79.3 MPa	ASTM D638
Tensile Elongation (Break)	3.0 %	3.0 %	ASTM D638
Flexural Modulus	800000 psi	5520 MPa	ASTM D790
Flexural Strength	12500 psi	86.2 MPa	ASTM D790
Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact (0.125 in (3.18 mm))	1.4 ft-lb/in	75 J/m	ASTM D256
Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load 264 psi (1.8 MPa), Unannealed	290 °F	143 °C	ASTM D648

**Notes**

These are typical property values not to be construed as specification limits.