

Technical Data Sheet

CirculenRecover PP300U Ivory HP

Polypropylene, Impact Copolymer

Product Description

CirculenRecover PP300U Ivory HP is a circular polypropylene copolymer supplied in pellet form for injection moulding applications. The grade combines very high flow, stiffness and impact. The grade is available in ivory color sorted from municipal plastic waste. ROHS declaration is available on request.

Sustainability

According with the requirements of Standard ISO 14021:2016, *CirculenRecover* PP300U Ivory HP contains at least 98 % of recycled material that is fully based on Post-Consumer Waste (PCW) from pre-sorted municipal plastic waste. Filtration level is 150 µm. Volatiles according to ASTM D6980 @ 120 °C are < 0.2%.

This product is not intended for highly regulated applications including food contact, potable water contact, medical and pharmaceutical applications.

Application	Containers; Crates; Furniture; Pails; TWIM Non-food Containers
Market	Consumer Products; Rigid Packaging
Processing Method	Injection Molding
Attribute	General Purpose; Good Processability; High Flow; Impact Copolymer

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	70	g/10 min	ISO 1133-1
Density	0.915	g/cm ³	ISO 1183-1
Bulk Density	0.620	g/cm ³	ISO 60
Mechanical			
Tensile Modulus, (23 °C)	1200	MPa	ISO 527-1, -2
Tensile Strength, (23 °C)	26	MPa	ISO 527-1, -2
Tensile Strain at Break, (23 °C)	10	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched, (23 °C, Type 1, Edgewise, Notch A)	4.0	kJ/m ²	ISO 179-1/1eA
Additional Information			
Ash 600 °C	< 2	wt %	ISO 3451-1