

Technical Data Sheet

Moplen EP340K



Polypropylene, Impact Copolymer

Product Description

Moplen EP340K is a nucleated impact copolymer suitable for injection moulding and thermoforming applications. Moplen EP340K exhibits an outstanding low temperature impact performance and good stiffness combined with a good processability.

Moplen EP340K is typically used by customers in luggage, transport and cold storage crates, sports and leisure equipment, toys and typical consumer components which are subjected to impact and/or low temperature.

This grade is not intended for medical and pharmaceutical applications.

Application	Caps & Closures; Crates; Luggage; Sports, Leisure & Toys
Market	Consumer Products; Rigid Packaging
Processing Method	Injection Molding; Thermoforming
Attribute	Good Processability; High Impact Resistance; Low Flow; Medium Stiffness; Nucleated

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	4	g/10 min	ISO 1133-1
Density	0.90	g/cm ³	ISO 1183-1
Mechanical			
Tensile Modulus	1100	MPa	ISO 527-1, -2
Tensile Stress at Yield	20	MPa	ISO 527-1, -2
Tensile Strain at Break	>50	%	ISO 527-1, -2
Tensile Strain at Yield	5	%	ISO 527-1, -2
Impact			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	66	kJ/m ²	ISO 179
(0 °C, Type 1, Edgewise, Notch A)	13	kJ/m ²	ISO 179
(-20 °C, Type 1, Edgewise, Notch A)	7	kJ/m ²	ISO 179
Ductile/Brittle Transition Temperature	-57	°C	ISO 6603-2
Hardness			
Ball Indentation Hardness	46	MPa	ISO 2039-1
Thermal			
Vicat Softening Temperature, (A50)	140	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	85	°C	ISO 75B-1, -2