

## Technical Data Sheet

### Moplen EP548S



Polypropylene, Impact Copolymer

#### Product Description

Moplen EP548S is a nucleated heterophasic copolymer with antistatic agent used injection moulding applications.

It combines a good impact/stiffness balance with a high fluidity.

Moplen EP548S is typically used by customers in opaque containers, housewares, toys and in thin-walled containers for food packaging (e.g. margarine tubs, yoghurt pots, etc.).

<b>Application</b>	Housewares; Opaque Containers; Sports, Leisure & Toys
<b>Market</b>	Consumer Products; Rigid Packaging
<b>Processing Method</b>	Injection Molding
<b>Attribute</b>	Contains Antistat; High Flow; Impact Copolymer; Nucleated

Typical Properties	Nominal Value	Units	Test Method
<b>Physical</b>			
Melt Flow Rate, (230 °C/2.16 kg)	44	g/10 min	ISO 1133-1
Density	0.90	g/cm <sup>3</sup>	ISO 1183-1
<b>Mechanical</b>			
Tensile Modulus	1550	MPa	ISO 527-1, -2
Tensile Stress at Yield	28	MPa	ISO 527-1, -2
Tensile Strain at Break	30	%	ISO 527-1, -2
Tensile Strain at Yield	5	%	ISO 527-1, -2
<b>Impact</b>			
Charpy Impact Strength - Notched			
(23 °C, Type 1, Edgewise, Notch A)	5	kJ/m <sup>2</sup>	ISO 179
(0 °C, Type 1, Edgewise, Notch A)	3.5	kJ/m <sup>2</sup>	ISO 179
(-20 °C, Type 1, Edgewise, Notch A)	3	kJ/m <sup>2</sup>	ISO 179
Ductile/Brittle Transition Temperature	-53	°C	ISO 6603-2
<b>Thermal</b>			
Vicat Softening Temperature, (A/50)	151	°C	ISO 306
Deflection Temperature Under Load, (0.45 MPa, Unannealed)	95	°C	ISO 75B-1, -2