

Technical Data Sheet

Polyfort PP 1692U-6955 STRYKER BUE



Polypropylene, Impact Copolymer

Product Description

Polyfort PP 1692 is an exceptional high impact copolymer with high flow for appearance parts. This material is available in Natural.

Processing Method	Compounding; Injection Molding
Attribute	High Flow; High Impact Resistance; Impact Copolymer
Forms	Pellets
Appearance	Natural Color

Typical Properties	Nominal Value	Units	Test Method
Physical			
Melt Flow Rate, (230 °C/2.16 kg)	20	g/10 min	ASTM D1238
Density - Specific Gravity	0.9	g/cm ³	ASTM D792
Mechanical			
Tensile Elongation at Yield, (3.20 mm, Injection Molded)	6.0	%	ASTM D638
Tensile Strength at Yield, (51 mm/min, 3.20 mm, Injection Molded)	24.2	MPa	ASTM D638
Flexural Modulus, (3.20 mm, Injection Molded, 1% Secant)	1100	MPa	ASTM D790
Impact			
Gardner Impact, (-30 °C)	24.7	J	ASTM D3029
Notched Izod Impact, (23 °C, 3.20 mm, Injection Molded)	>530	J/m	ASTM D256
Thermal			
Deflection Temperature Under Load Unannealed (66 psi)	105	°C	ASTM D648