

Technical Data Sheet

QR Resin QR-4100-GF30

Polyphenylene Ether + PS
Engineering Plastics

General	
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Good Stiffness • High Heat Resistance
Appearance	• Colors Available • Natural Color
Forms	• Pellets

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.28	1.28 g/cm ³	ASTM D792
Molding Shrinkage - Flow (0.125 in (3.18 mm))	1.0E-3 to 4.0E-3 in/in	0.10 to 0.40 %	ASTM D955

Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength (Yield)	15000 psi	103 MPa	ASTM D638
Flexural Modulus	1.00E+6 psi	6890 MPa	ASTM D790
Flexural Strength (Yield)	23000 psi	159 MPa	ASTM D790

Impact	Nominal Value (English)	Nominal Value (SI)	Test Method
Notched Izod Impact			ASTM D256
-22°F (-30°C)	1.8 ft·lb/in	96 J/m	
73°F (23°C)	2.0 ft·lb/in	110 J/m	

Thermal	Nominal Value (English)	Nominal Value (SI)	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi (0.45 MPa), Unannealed	315 °F	157 °C	
264 psi (1.8 MPa), Unannealed	275 °F	135 °C	

Technical Data Sheet

QR Resin QR-4100-GF30

Polyphenylene Ether + PS
Engineering Plastics



Injection	Nominal Value (English)	Nominal Value (SI)
Drying Temperature	225 °F	107 °C
Drying Time	3.0 to 4.0 hr	3.0 to 4.0 hr
Drying Time, Maximum	4.0 hr	4.0 hr
Rear Temperature	510 to 580 °F	266 to 304 °C
Middle Temperature	520 to 590 °F	271 to 310 °C
Front Temperature	560 to 600 °F	293 to 316 °C
Nozzle Temperature	560 to 600 °F	293 to 316 °C
Processing (Melt) Temp	560 to 600 °F	293 to 316 °C
Mold Temperature	170 to 220 °F	77 to 104 °C

Notes

These are typical property values not to be construed as specification limits.