HK:+852-69575415 China GuangDong:+13538586433 ShangHai:+18816996168

Technical Data Sheet

Polyvin PVC 9020N

Flexible Polyvinyl Chloride
LyondellBasell Industries
Engineering Plastics

Product Description
Flexible PVC formulation for general purpose molding applications requiring good dry touch, excellent weathering and ease of processing.

General		
Processing Method	• Extrusion	• Injection Molding

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.32	1.32 g/cm³	ASTM D792
Mechanical	**Nominal Value (English)**	**Nominal Value (SI)**	**Test Method**
Tensile Strength [1] (Yield)	2000 psi	13.8 MPa	ASTM D638
Tensile Elongation [1] (Break)	> 150 %	> 150 %	ASTM D638
Elastomers	**Nominal Value (English)**	**Nominal Value (SI)**	**Test Method**
Tear Strength [2]	> 45.1 lbf/in	> 7.90 kN/m	ASTM D624
Hardness	**Nominal Value (English)**	**Nominal Value (SI)**	**Test Method**
Durometer Hardness (Shore A, 15 Sec)	88	88	ASTM D2240

Notes

[1] Type IV, 20 in/min (510 mm/min)

[2] Die C, 2.0 in/min (51 mm/min)

Notes

These are typical property values not to be construed as specification limits.