

Technical Data Sheet

Polyvin PVC 9031D

Flexible Polyvinyl Chloride
 LyondellBasell Industries
 Engineering Plastics

Product Description

Flexible PVC formulation for interior molding applications requiring good dry touch, excellent weathering and ease of processing.

General

- | | |
|---------------------------|----------------------|
| Automotive Specifications | • FORD WSB-M4D871-A4 |
| Processing Method | • Injection Molding |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.35	1.35 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	1800 psi	12.4 MPa	ASTM D638
Tensile Elongation ¹ (Break)	250 %	250 %	ASTM D638
Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tear Strength ²	228 lbf/in	40.0 kN/m	ASTM D624
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore A, 15 Sec)	85	85	ASTM D2240

Notes

- ¹ Type IV, 20 in/min (510 mm/min)
- ² 20 in/min (500 mm/min)

Notes

These are typical property values not to be construed as specification limits.