

Technical Data Sheet

Polyvin PVC 9419D

Polyvinyl Chloride
LyondellBasell Industries
Engineering Plastics

Product Description

Low Gloss PVC 93A

General

- | | |
|-------------------|---------------------|
| Features | • Low Gloss |
| Processing Method | • Injection Molding |

Physical	Nominal Value (English)	Nominal Value (SI)	Test Method
Density / Specific Gravity	1.39	1.39 g/cm ³	ASTM D792
Mechanical	Nominal Value (English)	Nominal Value (SI)	Test Method
Tensile Strength ¹ (Yield)	1380 psi	9.50 MPa	ASTM D638
Tensile Elongation ¹ (Break)	120 %	120 %	ASTM D638
Elastomers	Nominal Value (English)	Nominal Value (SI)	Test Method
Tear Strength ²	160 lbf/in	28.0 kN/m	ASTM D1004
Hardness	Nominal Value (English)	Nominal Value (SI)	Test Method
Durometer Hardness (Shore A)	90	90	ASTM D2240

Notes

- ¹ 20 in/min (500 mm/min)
- ² 2.0 in/min (50 mm/min)

Notes

These are typical property values not to be construed as specification limits.